

Natural Asphalt – South America

Property	Method	Min Value	Max Value	Typical Value
% Fixed Carbon	ASTM D3172	----	12.00	11.82
% Ash	ASTM D3174	----	1.10	0.92
% Moisture	ASTM D3302	----	0.78	0.60
% Sulfur	ASTM D4239	----	3.98	3.85
% Carbon	ASTM D5373	83.00	86.00	84.18
% Nitrogen	ASTM D5373	1.15	1.40	1.24
% Hydrogen	ASTM D5373	8.20	9.20	9.02
Softening Point	ASTM E28-92	145.00	175.00	165 *C
Specific Gravity	ASTM D3289	1.04	1.10	1.06
Grain Size				Upto 300 Mesh

Origin:- South America

