

Oxidised Bitumen Specifications

Grade 85/25

PROPERTY	SPECIFICATION	TEST METHOD ASTM/EN13304
<i>SPECIFIC GRAVITY @ 25/25 CG</i>	1.01/1.06	D-70
<i>PENETRATION @ 25 C</i>	20/30	D-5
<i>SOFTENING POINT C</i>	80/90	D-36
<i>LOSS ON HEATING(WT) %</i>	0.2 MAX	D-6
<i>FLASH POINT C</i>	250 MIN	D-92
<i>SOLUBILITY IS CS2(WT) %</i>	99.5 MAX	D-4
<i>SPOT TEST</i>	NEGATIVE	A.A.S.H.O.T102

Grade 90/15

PROPERTY	SPECIFICATION	TEST METHOD ASTM/EN13304
<i>SPECIFIC GRAVITY @ 25/25 CG</i>	1.01/1.06	D-70
<i>PENETRATION @ 25 C</i>	10/20	D-5
<i>SOFTENING POINT C</i>	85/95	D-36
<i>LOSS ON HEATING(WT) %</i>	0.2 MAX	D-6
<i>FLASH POINT C</i>	250 MIN	D-92
<i>SOLUBILITY IS CS2(WT) %</i>	99.5 MAX	D-4
<i>SPOT TEST</i>	NEGATIVE	A.A.S.H.O.T102

Grade 115/15

PROPERTY	SPECIFICATION	TEST METHOD ASTM/EN13304
<i>SPECIFIC GRAVITY @ 25/25 CG</i>	1.01/1.06	D-70
<i>PENETRATION @ 25 C</i>	20/30	D-5
<i>SOFTENING POINT C</i>	70/80	D-36
<i>LOSS ON HEATING(WT) %</i>	0.2 MAX	D-6
<i>FLASH POINT C</i>	250 MIN	D-92
<i>SOLUBILITY IS CS2(WT) %</i>	99.5 MAX	D-4
<i>SPOT TEST</i>	NEGATIVE	A.A.S.H.O.T102