

PVC RESIN GRADE K

Grade	Appearance	Polymerization degree	Bulk Density	Volatile matter	Foreign matters
SE (K-57)	White	700±30	0.53-0.59	0.3%	30
SR (K-60)	White	800±40	0.52-0.58	0.3%	30
SL-K(K-66)	White	1030±40	0.53-0.57	0.3%	30
SL-P(K-66)	White	1030±40	0.47-0.53	0.3%	30
SM (K-72)	White	1300±50	0.46-0.52	0.3%	30
SD -7 (K-57)	White	700±70	0.44-0.50	0.3%	30
SD -10 (K-65)	White	1000±100	0.39-0.45	0.3%	30
SD -13 (K-72)	White	1300±150	0.37-0.43	0.3%	30
MR (K-60)	White	800±50	0.54-0.60	1.0%	30
ML (K-68)	White	1000±70	0.53-0.59	0.4%	30
MH (K-75)	White	1500±100	0.47-0.53	0.4%	30
CK (K-79)	White	1800±100	0.39-0.45	0.3%	30
CL (K-85)	White	2500±100	0.37-0.43	0.3%	30

Origin: Iran